

12

AD-A232 696

OFFICE OF NAVAL RESEARCH

Grant # N0001489J1848

R&T Code 413n003

Technical Report No. 3

Oxidation Studies of Fluorine  
Containing Diamond Films

by

K.J. Grannen, D.V. Tsu,  
R.J. Meilunas and R.P.H. Chang

Prepared for publication

in the


Applied Physics Letters

Northwestern University  
Department of Materials  
Science and Engineering  
Evanston, IL 60208

Feb. 26, 1991

Reproduction in whole or in part is permitted for any  
purpose of the United States Government

This document has been approved for public release and sale;  
its distribution is unlimited



Accession For	
NTIS GRA&I	<input checked="checked" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	



**DTIC**  
**ELECTE**  
MAR 08 1991  
**S E D**

91 3 07 078

## REPORT DOCUMENTATION PAGE

1a REPORT SECURITY CLASSIFICATION Unclassified			1b. RESTRICTIVE MARKINGS		
2a SECURITY CLASSIFICATION AUTHORITY			3 DISTRIBUTION/AVAILABILITY OF REPORT Approved for public release; distribution unlimited		
2b DECLASSIFICATION/DOWNGRADING SCHEDULE					
4 PERFORMING ORGANIZATION REPORT NUMBER(S) Technical Report number 3			5. MONITORING ORGANIZATION REPORT NUMBER(S)		
6a NAME OF PERFORMING ORGANIZATION Northwestern University R.P.H. Chang		6b OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION Office of Naval Research		
6c ADDRESS (City, State, and ZIP Code) Materials Science & Engineering Department Evanston, IL 60208			7b ADDRESS (City, State, and ZIP Code) Chemistry Division 800 N. Quincy Street Arlington, VA 22217		
8a. NAME OF FUNDING/SPONSORING ORGANIZATION Same as Monitoring Org.		8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER Grant # N0001489J1848		
8c. ADDRESS (City, State, and ZIP Code)			10 SOURCE OF FUNDING NUMBERS		
			PROGRAM ELEMENT NO	PROJECT NO	TASK NO
11 TITLE (Include Security Classification) Oxidation Studies of Fluorine Containing Diamond Films					
12 PERSONAL AUTHOR(S) K.J. Grannen, D.V. Tsu, R.J. Meilunas and R.P.H. Chang					
13a. TYPE OF REPORT Technical		13b. TIME COVERED FROM _____ TO _____		14 DATE OF REPORT (Year, Month, Day) Feb. 26, 1991	
15 PAGE COUNT 18					
16 SUPPLEMENTARY NOTATION					
17 COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP			
19 ABSTRACT (Continue on reverse if necessary and identify by block number)  The thermogravimetric method is used to study the oxidation properties of plasma grown diamond films both with and without fluorine. The oxidation experiments are carried out over a temperature range of 600°C - 800°C and in pure oxygen at one atmospheric pressure. Our experiments show diamond films with fluorine are more resistant (by as much as a factor of 4 at 700°C) to oxidation. The activation energy for oxidation, on the other hand, is at least a factor of 2.3 lower for diamond films with fluorine. These results lead us to postulate that oxidation mechanisms for diamond films are quite different depending on whether there is fluorine or not. For diamond films without fluorine the oxidation seems to proceed as a rate limited reaction, while for films with fluorine the oxidation seems to be a diffusion limited reaction. We have also found that there is a weak dependence of oxidation rates on film density, crystal texture, and the phase composition of the diamond film.					
20 DISTRIBUTION/AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS			21 ABSTRACT SECURITY CLASSIFICATION Unclassified		
22a NAME OF RESPONSIBLE INDIVIDUAL Dr. Mark Ross			22b TELEPHONE (Include Area Code) 703-696-4410		22c. OFFICE SYMBOL

## **Oxidation Studies of Fluorine Containing Diamond Films**

**K.J. Grannen, D.V. Tsu, R.J. Meilunas, and R.P.H. Chang**

**Department of Materials Science and Engineering**

**Northwestern University**

**Evanston, IL 60208**

### **Abstract**

The thermogravimetric method is used to study the oxidation properties of plasma grown diamond films both with and without fluorine. The oxidation experiments are carried out over a temperature range of 600°C - 800°C and in pure oxygen at one atmospheric pressure. Our experiments show diamond films with fluorine are more resistant (by as much as a factor of 4 at 700°C) to oxidation. The activation energy for oxidation, on the other hand, is at least a factor of 2.3 lower for diamond films with fluorine. These results lead us to postulate that oxidation mechanisms for diamond films are quite different depending on whether there is fluorine or not. For diamond films without fluorine the oxidation seems to proceed as a rate limited reaction, while for films with fluorine the oxidation seems to be a diffusion limited reaction. We have also found that there is a weak dependence of oxidation rates on film density, crystal texture, and the phase composition of the diamond film.

The success in chemical vapor deposition of polycrystalline diamond films has opened the way for potential application of these films as protective coatings on a variety of substrate materials. For example, it has recently been shown that diamond films on steel surfaces can successfully resist corrosion [ 1 ]. Diamond films have also been proven to be good optical coating materials which can resist mechanical wear [ 2 ]. However, there are instances where diamond films will be subjected to an oxygen containing

ambient at high temperatures. In such an environment it is noted that diamond will be readily oxidized (or vaporized) [ 3 ]. In fact, it has been shown that diamond oxidizes much more readily compared to graphite (which has a large fraction of its carbon atoms in double bond configuration) [ 4 ]. On the other hand, most chemical vapor deposited diamond films are composed of C - C or C - H bonds with average bond energies of 348 kJ/mol and 413 kJ/mol respectively [ 5 ]. It has also been shown recently that diamond films require more energy input to oxidize, compared to bulk diamond with comparable defect density [ 6 ]. Patterson et. al. have demonstrated that diamond powder (or grit), single crystal diamonds, as well as chemical vapor deposited (CVD) diamond films, can be fluorinated directly. By means of infrared and photon electron spectroscopy, they have shown that in most instances the fluorine is attached to the external surface. Once fluorinated, they find single crystal diamond slabs show enhanced resistance to further oxidation. In this article we study the oxidation resistance of diamond films which have incorporated fluorine during film nucleation and growth, and compare them with those that have not. What is the rationale for fluorinating diamond films to enhance oxidation resistance at high temperatures?

Recent experiments with slow positrons by Uedono et al and Sharma et al have shown that diamond films deposited with a microwave plasma can have defect densities as much as 0.4% and with void size of the order of 2 - 5Å [ 8 ]. Since etching process (in this case oxidation) propagates most readily along defects in

crystals, it is important that we terminate as many dangling bonds as possible on the internal surfaces of the defect voids and the external surfaces of the diamond films. To enhance oxidation resistance, it is necessary to convert as many surface carbon - carbon bonds and carbon - hydrogen bonds as possible to some stronger carbon bonds.

The strength of the C - F bond is 485 kJ/mol and fluorine atoms are small enough to fit easily in the defect voids of the diamond films. Fluorine can be easily formed in a plasma, and by using  $\text{CF}_4$  as a source we get both carbon and fluorine atoms for diamond film deposition. In the experiments reported here we have attempted to incorporate the amount of fluorine which is comparable to the defect (void) density of the diamond film. The rationale is to try to provide sufficient fluorine atoms to terminate a large fraction of dangling bonds of carbon atoms in the defect voids and on the surfaces. We anticipate such films with fluorine are more resistant to oxidation than films with internal and external surfaces covered mostly with hydrogen.

The experiments are performed in our microwave plasma deposition systems described elsewhere [ 9 ]. Typical deposition conditions are as follows: total gas flow rates between 100 and 200 sccm; gas composition 3%, 6%, 9%  $\text{CF}_4$  or 1/2%  $\text{CH}_4$  with a balance of 1/2%  $\text{O}_2$  and  $\text{H}_2$ ; total gas pressure 30 torr; microwave power 350-400W; substrate temperature 850°C-950°C. Silicon wafers, both (100) and (111) orientations are polished with 0.25  $\mu\text{m}$  diamond powder and cut to 1 cm by 1 cm in size. A variety of films several microns

thick are grown both with pure  $\text{CH}_4$  and  $\text{CF}_4$ . The surface morphologies are examined with scanning electron microscope (SEM) and the carbon phase information of the film is obtained by Raman spectroscopy. From the Raman spectra, one can not differentiate between diamond films grown from  $\text{CH}_4$  or  $\text{CF}_4$ . However, the SEM photos show a difference in surface morphology for diamond films grown at the same temperature. For example, films grown with  $\text{CH}_4$  at  $875^\circ\text{C}$  show triangular faceted surface, while  $\text{CF}_4$  grown films have continuous and rather smooth surfaces.

The amount of fluorine that has been incorporated in the diamond film is measured quantitatively to within a factor of 2, using secondary ion mass spectroscopy (SIMS) at the Charles Evans & Associates. All of the diamond films contain a few percent of hydrogen and a fraction of a percent of oxygen in addition to carbon. Films grown with  $\text{CF}_4$  typically have on the average  $10^{19} \text{ cm}^{-3}$  of fluorine distributed throughout the film.

After a diamond film is grown, the silicon substrate is removed in a solution of 3:3:5  $\text{HF}:\text{HNO}_3:\text{CH}_3\text{COOH}$  etchant before performing the thermogravimetric analysis (TGA) experiment. The oxidation of diamond films takes place in a Perkin-Elmer TGA instrument which we have interfaced with a personal computer. Pure oxygen flows into the oxidation chamber at a rate of 40 sccm. The chamber is at atmospheric pressure. Data acquisition is done through the use of a customized program. Average values for both the weight and temperature are obtained each second for the duration of the oxidation experiment by measuring every 2ms for the

first 150ms of each second, and averaging those 75 values together. The typical diamond film sample weighs between 0.2 to 0.6 milligram, while the noise level of our detection is 1 bit ( $= 1.5 \times 10^{-5}$  gram) for the 16 bit converter. In a typical oxidation experiment the temperature is manually ramped up to 700°C in approximately fifteen minutes and held at that temperature (700°C) for the duration of the diamond etching. From the weight loss curves, derivatives are taken to determine the etch rates as a function of time for various diamond growth conditions. Figure 1 shows etch rate plots of four different diamond films grown with different carbon gas sources and concentrations. The relative etch rates decrease, going from  $\text{CH}_4$  to  $\text{CF}_4$  sources with similar etch rates for 3% and 6%  $\text{CF}_4$  concentrations. From these plots we note that diamond films formed from either 3% or 6%  $\text{CF}_4$  gas source have etch rates about 1/4 of that of diamond films grown with 1/2%  $\text{CH}_4$  gas source at about 700°C. (Note, we have compared etch rates of films with comparable Raman spectra.)

In figure 2 we plot the etch rates as a function of the oxidation temperature for graphite, diamond powder ( $1/4 \mu\text{m}$  in size from Mega Diamond), and plasma deposited diamond films of three different morphologies, using  $\text{CH}_4$  gas source. We note the following etch behavior: for a given etch rate diamond powder (O) takes place at the lowest temperature, while graphite (◆) has the highest temperature, and the  $\text{CH}_4$  grown diamond films have temperatures in between the first two. The slope for the faceted diamond film (X) is close to that of the diamond powder, while the

cauliflower textured diamond film ( $\Delta$ ) has a slope close to that of graphite. On the other hand, a  $\text{CH}_4$  grown film ( $\diamond$ , grown at a much slower rate or a more compact film) with very strong diamond Raman signal and a minimal detectable graphitic signal has a slope in between. The activation energy as measured from the plot for diamond powder is about 6.5 eV, while the activation energy for graphite is about 3.1 eV, and the activation energy of the  $\text{CH}_4$  grown diamond films are between 4 eV and 4.7 eV. From these plots we see there is not much dependance of the etch rate on surface morphology of the films until the temperature is close to 700°C. At this temperature it is known that hydrogen atoms which passivate the diamond surfaces thermally desorb appreciably.

The etch rates as a function of temperature for diamond films grown with  $\text{CF}_4$  gas source is plotted in figure 3. We note that the slopes of these curves (or the activation energies) are about a factor of 2.3 lower than the films grown with  $\text{CH}_4$  gas source. There does not seem to be any difference in the etch rate curves between that deposited with 3% ( $\square$ ) and 6% ( $\blacklozenge$ )  $\text{CF}_4$ , neither is there an etch rate difference between films with different texture or morphology of the films. For instance, sample ( $\square$ ) is a faceted film while sample ( $\circ$ ) is a non-faceted film grown with 3%  $\text{CF}_4$  but different substrate temperatures. With 9%  $\text{CF}_4$  as a source, the etch rate curve shifts slightly up but the shape is well preserved. Comparing  $\text{CF}_4$  grown films with  $\text{CH}_4$  grown films, we see that films grown from  $\text{CH}_4$  (X) etch 4 times faster than  $\text{CF}_4$  grown diamond films at about 700°C. But at lower temperatures, below 600°C, the  $\text{CF}_4$



grown films seem to etch faster.

We like to postulate an explanation to our experimental observation. In the case of diamond films without fluorine, we note the activation energy is around 4 eV, which is close to the energy value of single covalent bond of carbon. Thus, similar to the case of either oxidation of silicon or plasma etching of silicon, the oxidation (i.e. etching) of these diamond films is dominated by the surface reaction process. The etch rate is reaction limited. On the other hand, we believe that diamond films with fluorine have their surface covered with fluorine-carbon bonds (recent measurements by Freedman and Stinespring support this argument [ 10 ]) and, perhaps, a fraction of the internal interfaces as well. In the high temperature regime (around 700°C), the surface reaction with oxygen proceeds much slower, compared to the case when the surface is covered with hydrogen-carbon bonds (i.e. the case of diamond film with no fluorine). But as we have noted earlier, diamond films have a large percentage of defects and grain boundaries, so oxygen will diffuse readily into the internal boundaries and voids to etch the diamond film. Thus we believe for the case of fluorine containing diamond film, the reaction is diffusion limited and hence a lower activation energy (around 2 eV). This is possible because not all of the internal surfaces have fluorine bonds (but rather a large portion with hydrogen bonds or simple carbon-carbon bonds or dangling bonds). During oxidation at temperatures around 700°C, a larger fraction (comparing to fluorine) of the hydrogen will have been thermally

desorbed and reacted with oxygen, thus etching from within the film. At this point we do not have enough data to give a quantitative explanation of our observation.

In conclusion, we have shown that diamond films with fluorine etch much slower at high temperatures than diamond films without fluorine. We believe this is due to the termination of surface and a fraction of the internal surface (inside the defect voids) by fluorine atoms. The amount of fluorine incorporation is comparable to the density of defects as reported by slow positron measurements.

#### Acknowledgement

We thank T.P. Ong for his help with the experiment, and valuable discussions with Drs. R.H. Hauge, J.L. Margrave, and S. C. Sharma during the early stages of our experiments. This project is supported by the Office of Naval Research. The measurements were performed in Materials Research Center Facilities, supported by the NSF/MRL Program. We thank Mr. Stephen Smith of Charles Evans for performing the SIMS measurements.

#### References

1. T.P. Ong, R.P.H. Chang, Appl. Phys. Lett. 58, 28 Jan. (1991).
2. T.P. Ong, R.P.H. Chang, Appl. Phys. Lett. 55, 2063 (1989).
3. A. Joshi, R. Nimmagadda, J. Herrington, J. Vac. Sci. Technol. A8, 2137 (1990).
4. C. Johnson, W. Weimar, D. Harris, Mater. Res. Bull. 24, 1127

(1990)

5. T.L. Brown, H.E. LeMay, *Chemistry: The Central Science*, (Prentice-Hall, Englewood Cliff, NJ, 1981), p. 190.
6. R.R. Nimmagadda, A. Joshi, W.L. Hsu, *J. Mater. Res.* 5, 2445 (1990).
7. D. E. Patterson, R. H. Hauge, and J. L. Margrave, *Mat. Res. Soc. Symp. Proc.* Vol 140, 351, (1989)
8. A. Uedono, S. Tanigawa, H. Funamoto, A. Nishikawa, K. Takahashi, *Jpn. J. Appl. Phys.* 29, 555 (1990); S.C. Sharma, C.A. Dark, R.C. Hyer, M. Green, T.D. Black, A.R. Chourasia, D.R. Chopra, K.K. Misha, *Appl. Phys. Lett.* 56, 1781 (1990).
9. R. Meilunas, M.S. Wong, K.C. Sheng, T.P. Ong and R.P.H. Chang, in *Laser and Particle Beam Chemical Processes*, MRS Proc. Vol. 129, edited by A.W. Johnson, C.L. Loper and T.W. Sigmon (Materials Research Society, Pittsburgh, 1987).
10. A. Freedman and C. D. Stinespring, *Appl. Phys. Lett.* 57, 1194 (1990).


#### Figure Caption


Figure 1. Relative etch rate plots for diamond films grown with three different concentrations of  $CF_4$  and 1/2%  $CH_4$ .


Figure 2. Arrhenius plot for various forms of carbon: (♦) graphite; (▲) diamond film grown with 1/2%  $CH_4$  with cauliflower surface texture; (◊) diamond film grown with 1/2%  $CH_4$  densely packed crystalline surface; (X) diamond film grown with 1/2%  $CH_4$  with well

faceted surface; (O) 0.25  $\mu\text{m}$  diamond powder.

Figure 3. Arrhenius plot for a variety of diamond films: ( $\square$ ) is a faceted film grown with 3%  $\text{CF}_4$ ; (O) is a non-faceted film grown with 3%  $\text{CF}_4$ ; ( $\diamond$ ) is a film grown with 6%  $\text{CF}_4$ ; (+) is a film grown with 9%  $\text{CF}_4$ ; and (X) is a film grown with 1/2%  $\text{CH}_4$ .







## DISTRIBUTION LIST

Mr. James Arendt  
Hughes Aircraft Company  
8433 Fallbrook Ave. 270/072  
Canoga Park, CA 91304  
(818) 702-2890

Mr. Larry Blow  
General Dynamics  
1525 Wilson Blvd., Suite 1200  
Arlington, VA 22209  
(703) 284-9107

Mr. Ellis Boudreaux  
Code AGA  
Air Force Armament Laboratory  
Eglin AFB, FL 32542

Dr. Duncan Brown  
Advanced Technology Materials, Inc.  
520-B Danbury Road  
New Milford, CT 06776

Dr. Mark A. Cappelli  
Mechanical Engineering Dept.  
Stanford University  
Stanford, CA 94305  
(415) 723-1745

Dr. R. P. H. Chang  
Materials Science & Engineering Dept.  
2145 Sheridan Road  
Evanston, IL 60208  
(312) 491-3598

Defense Documentation Center  
Cameron Station  
Alexandria, VA 22314  
(12 copies)

Dr. Albert Feldman  
Leader, Optical Materials Group  
Ceramics Division  
Materials Science & Engineering Laboratory  
NIST  
Gaithersburg, MD 20899  
(301) 975-5740

Dr. John Field  
Department of Physics  
University of Cambridge  
Cavendish Laboratory  
Madingley Road  
Cambridge CB3 0HE  
England  
44-223-337733, ext. 7318

Dr. David Goodwin  
Mechanical Engineering Dept.  
California Institute of Technology  
Pasadena, CA 91125  
(818) 356-4249

Dr. Kevin Gray  
Norton Company  
Goddard Road  
Northboro, MA 01532  
(508) 393-5968

Mr. Gordon Griffith  
WRDC/MLPL  
Wright-Patterson AFB, OH 45433

Dr. H. Guard  
Office of Chief of Naval Research  
Office of Naval Research (Code 1113PO)  
800 North Quincy Street  
Arlington, VA 22217

Dr. Alan Harker  
Rockwell Int'l Science Center  
1049 Camino Dos Rios  
P.O. Box 1085  
Thousand Oaks, CA 91360  
(805) 373-4131

Mr. Stephen J. Harris  
General Motors Research Laboratories  
Physical Chemistry Department  
30500 Mound Road  
Warren, MI 48090-9055  
(313) 986-1305



Dr. Rudolph A. Heinecke  
STC  
Laboratories, Ltd.  
London Road  
Harlow, Essex CM17 9MA  
England  
44-279-29531, ext. 2284

Dr. Curt E. Johnson  
Code 3854  
Naval Weapons Center  
China Lake, CA 93555-6001  
(619) 939-1631

Dr. Larry Kabacoff (Code R32)  
Officer in Charge  
Naval Surface Weapons Center  
White Oak Laboratory  
10901 New Hampshire  
Silver Spring, MD 20903-5000

Mr. M. Kinna  
Office of Chief of Naval Research  
Office of Naval Technology (Code 225)  
800 North Quincy Street  
Arlington, VA 22217

Dr. Paul Klocek  
Texas Instruments  
Manager Advanced Optical Materials Branch  
13531 North Central Expressway  
P.O. Box 655012, MS 72  
Dallas, Texas 75268  
(214) 995-6865

Ms. Carol R. Lewis  
Jet Propulsion Laboratory  
4800 Oak Grove Drive  
Mail Stop 303-308  
Pasadena, CA 91109  
(818) 354-3767

Dr. J. J. Mecholsky, Jr.  
256 Rhines Hall  
Materials Science & Engineering Dept.  
University of Florida  
Gainesville, FL 32611  
(904) 392-1454

Dr. Russ Messier  
Pennsylvania State University  
Materials Research Laboratory  
University Park, PA 16802  
(814) 865-2262

Mr. Mark Moran  
Code 3817  
Naval Weapons Center  
China Lake, CA 93555-6001

Mr. Ignacio Perez  
Naval Air Development Center  
Code 6063  
Warminster, PA 18974  
(215) 441-1681

Mr. C. Dale Perry  
U.S. Army Missile Command  
AMSMI-RD-ST-CM  
Redstone Arsenal, AL 35898-5247

Mr. Bill Phillips  
Crystallume  
125 Constitution Drive  
Menlo Park, CA 94025  
(415) 324-9681

Dr. Rishi Raj  
Materials Science & Engineering Dept.  
Cornell University  
Ithaca, NY 14853  
(607) 255-4040

Dr. M. Ross  
Office of Chief of Naval Research  
Office of Naval Research (Code 1113)  
800 North Quincy Street  
Arlington, VA 22217

Dr. Rustum Roy  
Pennsylvania State University  
Materials Research Laboratory  
University Park, PA 16802  
(814) 865-2262

Dr. J. Savage  
Royal Signals and Radar Establishment  
St. Andrews Road  
Great Malvern, WORCS, WR14 3PS  
England

Mr. David Siegel  
Office of Chief of Naval Research  
Office of Naval Research (Code 213)  
800 North Quincy Street  
Arlington, VA 22217

Dr. Keith Snail  
Code 6520  
Naval Research Laboratory  
Washington, D.C. 20375  
(202) 767-0390

Dr. Y. T. Tzeng  
Electrical Engineering Department  
Auburn University  
Auburn, AL 36849  
(205) 884-1869

Dr. George Walrafen  
Chemistry Department  
Howard University  
525 College Street, N.W.  
Washington, D.C. 20054  
(202) 806-6897/6564

Mr. Roger W. Whatmore  
Plessey Research Caswell Ltd.  
Towcester Northampton NN128EQ  
England  
(0327) 54760

Dr. Aaron Wold  
Chemistry Department  
Brown University  
Providence, RI 02912  
(401) 863-2857

Dr. Charles Willingham  
Raytheon Co.  
Research Division  
131 Spring Street  
Lexington, MA 02173  
(617) 860-3061

Dr. Robert E. Witkowski  
Westinghouse Electric Corporation  
1310 Beulah Road  
Pittsburgh, PA 15235  
(412) 256-1173

Mr. M. Yoder  
Office of Chief of Naval Research  
Office of Naval Research (Code 1114SS)  
800 North Quincy Street  
Arlington, VA 22217